
MB 1.0 CONCRETE



MB 1.0 DESCRIPTION

Highest temperature service novolac vinyl ester with special additives for flexibility and performance.



COMMON AREAS OF USE

- FGD duct work plate and structural steel
- +350°F (177°C) dry / +200°F (93°C) wet coal fired service

MB 1.0 DETAILS

Surface Preparation	SSPC-SP13 / NACE 6 - ICRI CSP 5 or greater		
Concrete Rehabilitation	Series <u>217</u> MortarCrete, Series <u>215</u> Surfacing Epoxy or Primer + Series <u>211-9111</u> Bulking Powder	As required.	As required.
Prime Coat (Stripe)	Series <u>1407</u> Vinester*	4-6 mils DFT	275 sq ft / gal
First Coat	Series <u>1438</u> Vinester	20 mils DFT	65 sq ft /gal
Finish Coat	Series <u>1438</u> Vinester	20 mils DFT	65 sq ft /gal
		45 mils DFT	

Published technical data, instructions and pricing are subject to change without notice. Contact your Tnemec technical representative for current technical data, instructions and pricing. Warranty information: The service life of Tnemec's coatings will vary. For warranty, limitation of seller's liability and product information, please refer to Tnemec Product Data Sheets at Imemec.com or contact your Tnemec technical representative. © Tnemec Company, Inc. MB10C

^{*}Do not use Series 1407 in wet or dry services of >180°F (82°C) or 200°F (93°C) spikes. Preference is direct-to-metal.

Note: Coverage rates are theoretical (no loss). Reference Tnemec data sheets, application guides and construction details for more information.