
MB 2.2 CONCRETE



MB 2.2 DESCRIPTION

High-molecular weight (HMW) novolac vinyl ester with a special abrasion and impact resistant finish coat.



COMMON AREAS OF USE

- High areas of impingement and dry conditions of up to 300°F (149°C)
- In wet slurry service for abrasion resistance

MB 2.2 DETAILS

Surface Preparation	SSPC-SP13 / NACE 6 - ICRI CSP 5 or greater		
Concrete Rehabilitation	Series <u>217</u> MortarCrete, Series <u>215</u> Surfacing Epoxy or Primer + Series <u>211-9111</u> Bulking Powder	As required.	As required.
Prime Coat (Stripe)	Series <u>1407</u> Vinester*	4-6 mils DFT	275 sq ft / gal
First Coat	Series <u>1436</u> Vinester	20 mils DFT	65 sq ft /gal
Finish Coat	Series <u>1439</u> Vinester	25 mils DFT	55 sq ft /gal
		50 mils DFT	

Published technical data, instructions and pricing are subject to change without notice. Contact your Tnemec technical representative for current technical data, instructions and pricing. Warranty information: The service life of Tnemec's coatings will vary. For warranty, limitation of seller's liability and product information, please refer to Tnemec Product Data Sheets at Imemec.com or contact your Tnemec technical representative. © Tnemec Company, Inc. MB22C

^{*}Do not use Series 1407 in wet or dry services of >180°F (82°C) or 200°F (93°C) spikes. Preference is direct-to-metal.

Note: Coverage rates are theoretical (no loss). Reference Tnemec data sheets, application guides and construction details for more information.