
MB 3.0 STEEL



MB 3.0 DESCRIPTION

An epoxy flake filled vinyl ester, inert flake-filled lining.



COMMON AREAS OF USE

- Industrial wastewater applications such as rake arms and equipment.
- Best for caustic services.

MB 3.0 DETAILS

Surface Preparation	SSPC-SP10 / NACE 2 / 3.0-mil minimum anchor profile		
Prime Coat (Stripe)	Series <u>1407</u> Vinester*	4-6 mils DFT	275 sq ft / gal
First Coat	Series <u>1430</u> Vinester	20 mils DFT	65 sq ft /gal
Finish Coat	Series <u>1430</u> Vinester	20 mils DFT	65 sq ft /gal
		45 mils DFT	

Published technical data, instructions and pricing are subject to change without notice. Contact your Tnemec technical representative for current technical data, instructions and pricing. Warranty information: The service life of Tnemec's coatings will vary. For warranty, limitation of seller's liability and product information, please refer to Tnemec Product Data Sheets at Imemec.com or contact your Tnemec technical representative. © Tnemec Company, Inc. MR30C

^{*}Do not use Series 1407 in wet or dry services of >180°F (82°C) or 200°F (93°C) spikes. Preference is direct-to-metal.

Note: Coverage rates are theoretical (no loss). Reference Tnemec data sheets, application guides and construction details for more information.