


## RS 1.2 DESCRIPTION

Epoxy vinyl ester lining system, reinforced with 1.5-oz. chopped strand mat and abrasion resistant finish coat.



## COMMON AREAS OF USE

- Secondary containment
- Reinforced lining system
- Minor crack bridging
- Slurry and dry service
- Extra abrasion resistance and release finish

## RS 1.2 DETAILS

<b>Surface Preparation</b>	SSPC-SP10 / NACE 2 / 3.0-mil minimum anchor profile	--	--
<b>Prime Coat (Stripe)</b>	Series <a href="#">1407</a> Vinester*	4-6 mils DFT	275 sq ft / gal
<b>Mortar Coat</b>	Series <a href="#">1415-900</a> Vinester + Series <a href="#">211-9111</a> Bulking Powder	60 mils DFT	45 sq ft / gal
<b>Mat</b>	Series <a href="#">211-227</a> 1.5-oz Chopped Strand Mat	--	--
<b>Saturant Coat</b>	Series <a href="#">1415-900</a> Vinester	20 mils DFT	60 sq ft / gal
<b>Finish Coat</b>	Series <a href="#">1439</a> Vinester	25 mils DFT	55 sq ft / gal

**95 mils DFT**

\*Do not use Series 1407 in wet or dry services of >180°F (82°C) or 200°F (93°C) spikes. Preference is direct-to-metal.

**Note:** Coverage rates are theoretical (no loss). Reference Tnemec data sheets, application guides and construction details for more information.

Published technical data, instructions and pricing are subject to change without notice. Contact your Tnemec technical representative for current technical data, instructions and pricing. Warranty information: The service life of Tnemec's coatings will vary. For warranty, limitation of seller's liability and product information, please refer to Tnemec Product Data Sheets at [tnemec.com](http://tnemec.com) or contact your Tnemec technical representative. © Tnemec Company, Inc. RS12S